

DECLARATION OF PERFORMANCE	
Reference :	DOPHydroFlamv1
Commercial name :	HydroFlam
Product type :	Fire retardant Particleboard
Reference standard :	Wood Based Panel - EN 13986 Annex A Table A.4
CE Class :	P5
Field of application :	Internal use as structural component in humid conditions
AVCP Class :	1
Certification number:	1161-CPR-1323
Produced at:	Ingelmunstersteenweg 299,B-8780 Oostrozebeke

Essential Characteristic	Unit	Reference	Thickness range (mm)		
			> 6-13	> 13-20	> 20-25
Bending strength	N/mm <sup>2</sup>	EN 312-table 7	18	16	14
Bending stiffness	N/mm <sup>2</sup>	EN 312-table 7	2550	2400	2150
Internal bond	N/mm <sup>2</sup>	EN 312-table 7	0,45	0,45	0,40
Swelling in thickness, 24h	%	EN 312-table 7	11	10	10
Moisture resistance OPTION 1 : Internal bond	N/mm <sup>2</sup>	EN 312-table 8	0,25	0,22	0,20
Moisture resistance OPTION 1 : Swelling in thickness	%	EN 312-table 8	12	12	11
Surface Soundness	N/mm <sup>2</sup>	EN 312-table 7	0	0	0
Formaldehyde emission class	Class	EN 13986-table B1	E1	E1	E1
Formaldehyde content	mg/100g	EN 120	≤ 8	≤ 8	≤ 8
Reaction to fire	Class	EN 13501-1	B-s2,d0	B-s2,d0	B-s2,d0
Reaction to fire	Class	BS 476	Class 1	Class 1	Class 1
Water vapour permeability μ	wet	EN 13986-table 9	16	16	15
	dry		50	50	50
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	NPD
Sound absorption α		EN 13986-table 10	0,10/0,25	0,10/0,25	0,10/0,25
Thermal conductivity λ	W/m.K	EN 13986-table 11	0,14	0,14	0,13
Strength - tension f <sub>t</sub>	N/mm <sup>2</sup>	EN 12369-1	9,4	8,5	7,4
Strength - compression f <sub>c</sub>	N/mm <sup>2</sup>	EN 12369-1	12,7	11,8	10,3
Strength - bending f <sub>m</sub>	N/mm <sup>2</sup>	EN 12369-1	15,0	13,3	11,7
Strength - panel shear f <sub>y</sub>	N/mm <sup>2</sup>	EN 12369-1	7,0	6,5	5,9
Strength - planar shear f <sub>r</sub>	N/mm <sup>2</sup>	EN 12369-1	1,9	1,7	1,5
Stiffness - tension E <sub>t</sub>	N/mm <sup>2</sup>	EN 12369-1	2000	1900	1800
Stiffness - compression E <sub>c</sub>	N/mm <sup>2</sup>	EN 12369-1	2000	1900	1800
Stiffness - bending E <sub>m</sub>	N/mm <sup>2</sup>	EN 12369-1	3500	3300	3000
Stiffness - panel shear G <sub>v</sub>	N/mm <sup>2</sup>	EN 12369-1	960	930	860
Impact resistance	Class	EN 12871	NPD	NPD	NPD
Linear expansion δ <sub>1,30,85</sub>	mm/m	EN 318	< 4	< 4	< 4
Mechanical durability (kmod; kdef)			EN 1991-1-1	EN 1991-1-1	EN 1991-1-1
Biological durability	Service Class	EN 335	1 & 2	1 & 2	1 & 2
Content of PCP	ppm	EN 13986-5.18	< 5	< 5	< 5

Version date :  
1/06/2014

Lode De Boe,  
President UNILIN bvba, division panels

